



Ultra Reflections Floor Finish

Green Certified



Purpose

Created to guide a person with steps for applying **Zing Ultra Reflections Floor Finish.**

Tools Required



Wet Floor Sign



1 oz. Pump



Zing Floor Prep



Microfiber Flat Mop Holder w/adjustable handle



Floor Finish Dispensing Valve



Medium Grade Hair Pad



1500 Zinger High Speed Burnisher



Microfiber Flat Mop Finish Applicator



Zing Ultra Reflections Floor Finish



Zing Dust Control



Zing CPC (Cleaning & Polishing Compound)



UV Pen Light



Back-pack Vacuum



18" Floor Tool



Pen Light




Automatic Scrubber



Mop & Bucket

Key Functions

Be sure and use a **Microfiber Finish Flat Mop with Microfiber Flat Mop Holder with adjustable handle.**



Apply **Zing Ultra Reflections Floor Finish** using a **Floor Finish Dispensing Valve** attached to the gallon of coating.



Prior to Re-Applying Additional Coats

Use an **8 1/2 x 11 copy paper** with no print to test for dry coating.

Place a new piece of **copy paper** on the floor where you stopped applying the coating. Place all your weight on one foot and the ball of your other foot lightly on the paper and move it forward and back. If the paper moves easily, the coating is ready for re-coating.

Note: If the paper drags in any way, the coating is not dry and ready for re-coating. *Never use the copy paper for more than one test, use a new piece each time you perform the test.*

Never apply more than 4 coats in a 24 hour period.

Procedures

Step 1 - Vacuum or dust mop with a treated **Zing Dust Control** treated mop.

Step 2 - Equip automatic scrubber with a **Medium Grade Hair Pad**. **Double scrub** floor with **Zing Floor Prep** diluted at 8 oz. per gallon with cold water.

Step 3 - High speed burnish clean floor with a 1500 RPM machine equipped with a *medium grade hair pad* and **Zing CPC (Cleaning and Polishing Compound)**.

Step 4 - Apply **Zing Ultra Reflections Floor Finish**, 1-3 Coats.

Step 5 - **Wash Coating Applicator Flat Mop 3 times before re-using.**
• **Next Area Repeat Above Steps 1-5** •

On stripped floors: Apply first coat, **Zing Ultra Reflections Floor Finish** as a sealer diluted 50% with water.



Apply **Ultra Reflections Finish** un-diluted after seal coat, until you have achieved the desired look. **Maximum 4 coats in a 24 hour period.**

For future Re-coating Application: dilute **Ultra Reflections 50%** with water. Example: 1 gallon **Ultra Reflections** to 1 gallon of water will make 2 gallons of **Ultra Reflections Finish**

For correct number of coats, check for quality reflection of light, using pen light.



Ultra Reflections Finish Wear Evaluation

Mark floor with application date after initial 50/50 seal coating.

S-50/50 = Seal 50/50 coat

Mark floor after each un-diluted coat C-1, C-2

C-1 = Un-diluted first coat.

C-2 = Un-diluted second coat.

Maximum 4 coats in 24 Hours.



Check periodically for wear with UV Pen Light.