



First Impression Coating Application and Wear Monitoring



Purpose

Designed to recommend the number of First Impression Coats and Wear Evaluation Process.

No. 546

All About Zing First Impression Coating

Zing First Impression Coating is designed to Synchronize the results obtained from using the complete Zing Science of Zing Floor Care Technology. Resists soil penetration. For use on all hard floor surfaces.

Apply Zing First Impression Coating using a Floor Finish Dispensing Valve attached to the gallon of coating.



Floor Preparation Procedures

Step 1 - Vacuum or dust mop with a **Zing Dust Control** treated mop.

Step 2 - Equip automatic scrubber with a **Medium Grade Hair Pad**. Double scrub floor with **Zing KLEEN-UP** diluted
6 oz. per gallon or **Zing Floor Prep** diluted at 8 oz. per gallon

Step 3 - High speed burnish clean floor with a 1500 RPM machine equipped with a **Medium Grade Hair Pad** and **Zing CPC (Cleaning and Polishing Compound)**.

Step 4 - Apply Zing First Impression Coating, 1-3 coats.

Step 5 - Wash coating applicator flat mop 3 times before re-using.

For stripping floors: Apply first coat, First Impression Coating as a sealer, diluted 50% with water.

Apply a Green 50/50 Coating label to gallon for future use. Apply First Impression Coating un-diluted after seal coat, until you have achieved the desired look.

Maximum 4 coats in a 24 hour period.

For future re-coating application: Dilute First Impression
Coating 50% with water: Example: 1 gallon First Impression
Coating To 1 gallon of water will make 2 gallons First Impression
Coating for re-coating.

For correct number of coats, check for quality reflection of light using Reflection Pen Light.

Reflection Pen Light

First Impression Coating Marking and Wear Evaluation

Mark floor with application date after initial 50/50 seal coating. <u>Example</u>: 01/14/18

S-50/50 = Seal 50/50 coat

Mark floor after each un-diluted coat C-1, C-2. Use a UV Marker to mark each coat after application.

UV Marker

C-1 = Un-diluted first coat.

C-2 = Un-diluted second coat.

Maximum 4 coats in 24 Hours.



Check periodically for wear with UV Pen Light.